

Description

A post-consumer recycled polystyrene, suitable for injection molding and often used for extrusion applications. Available in light grey(reference 90/02), signal grey (reference 70/04) and silk grey (reference 70/44).

Material Properties

	Value	Unit	Test Method
Physical			
Density	1.05	g/cm ³	MBA method
Rheological			
Melt Flow Rate (200°C / 5.0 kg)	6.5	g/10 min	ISO 1133
Mechanical			
Tensile Stress at Yield (23°C)	23	MPa	ISO 527-2/50
Impact			
Izod Impact Strength, notched (23°C)	8	kJ/m ²	ISO 180/1A
Charpy Impact Strength, notched (23°C)	8	kJ/m ²	ISO 179/1eA

Note:

The data above is provided in good faith and represents typical properties based on our current knowledge and experience. Product properties may be changed without notice. These properties are provided as a guide and should not be construed as binding specification limits or minimum values. This document does not create any liability, warranty or guarantee of product performance. It is the buyer's responsibility to determine the suitability of MBA Polymers products for the intended application.

Technical Data Sheet

EvoSource™ PS 3122 E



Processing Information

	Value	Unit
Preprocessing		
Drying Temperature	70	°C
Drying Time	1-2	hr
Moisture Content	<0.05-0.10	%
Injection Molding		
Melt Temperature Range	190-230	°C
Recommended Melt Temperature	220	°C
Mold Temperature Range	20-60	°C
Recommended Mold Temperature	40	°C
Recommended Screw Back Pressure	100-200	bar
Extrusion		
Melt Temperature Range	180-210	°C
Recommended Melt Temperature	200	°C

Note:

The processing parameters listed above are general guidelines based on our current knowledge and experience. The suitability of the data for a specific processing method can only be ensured with investigations and tests by the end user.